

380/380CB Series Recommended Cutting Data - Profile Milling Inch

Workpiece Material Group	ISO	Coolant			RWOC (Ae)		End Mill Diameter (inch)			
		Emulsion	Air	MQL	5%	10%	3/8	1/2	5/8	3/4
					2.3	1.67	← Multiply fz by this factor based on ae. When finishing, use the standard fz per chart below. Only add chip thinning when roughing or semi-finishing.			
					Vc - SFM					
Low Carbon Steels	P	○	●	○	1475	1150	.0023	.0030	.0038	.0045
Medium Carbon Steels		○	●	○	1130	900	.0023	.0030	.0038	.0045
Alloy Steels		○	●	○	1035	840	.0023	.0030	.0038	.0045
Die / Tool Steels		○	●	○	900	725	.0023	.0030	.0038	.0045
Free Machining Stainless Steels	M	●	●	○	675	545	.0023	.0030	.0038	.0045
Austenitic Stainless Steels		●	x	○	525	430	.0019	.0025	.0031	.0038
Difficult Stainless Steels		●	x	○	410	330	.0015	.0020	.0025	.0030
PH Stainless Steels		●	●	○	525	430	.0015	.0020	.0025	.0030
Cobalt Chrome Alloys		●	x	○	410	325	.0015	.0020	.0025	.0030
Duplex (22%)		●	x	○	330	295	.0015	.0020	.0025	.0030
Super Duplex (25%)		●	x	○	245	195	.0015	.0020	.0025	.0030
High Temp Alloys		S	●	x	x	180	150	.0009	.0013	.0016
Titanium Alloys	●		○	○	375	330	.0015	.0020	.0025	.0030
Gray Cast Irons	K	●	○	○	1625	1295	.0023	.0030	.0038	.0045
Ductile Cast Irons		●	○	○	975	885	.0023	.0030	.0038	.0045
Malleable Cast Irons		●	○	○	575	490	.0023	.0030	.0038	.0045
Hardened Steels 45-50 HRC	H	○	●	○	610	495	.0019	.0025	.0031	.0038
Hardened Steels 50-55 HRC		○	●	○	510	-	.0013	.0018	.0022	.0026
Hardened Steels 55-60 HRC		○	●	○	330	-	.0008	.0010	.0013	.0015

● Preferred ○ Possible x Not Possible

Notes:

- For machining materials above 50 HRC, reduce stepover (ae) to 2-3% of DC for optimal performance

Spindle Maximum - Should the calculated spindle speed be more than your actual spindle maximum, use this formula:
 (Calculated Feed x Spindle Maximum)/Calculated Speed.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.

380/380CB Series Recommended Cutting Data - Profile Milling Metric

Workpiece Material Group	ISO	Coolant			RWOC (Ae)		End Mill Diameter (mm)			
		Emulsion	Air	MQL	Diagram		10	12	16	20
							Multiply fz by this factor based on ae. When finishing, use the standard fz per chart below. Only add chip thinning when roughing or semi-finishing.			
					5%	10%				
Vc - SFM		fz - mm/tooth								
Low Carbon Steels	P	o	•	o	450	350	0.060	0.072	0.096	0.120
Medium Carbon Steels		o	•	o	345	275	0.060	0.072	0.096	0.120
Alloy Steels		o	•	o	315	255	0.060	0.072	0.096	0.120
Die / Tool Steels		o	•	o	275	220	0.060	0.072	0.096	0.120
Free Machining Stainless Steels	M	•	•	o	205	165	0.060	0.072	0.096	0.120
Austenitic Stainless Steels		•	x	o	160	130	0.050	0.060	0.080	0.100
Difficult Stainless Steels		•	x	o	125	100	0.040	0.048	0.064	0.080
PH Stainless Steels		•	•	o	160	130	0.040	0.048	0.064	0.080
Cobalt Chrome Alloys		•	x	o	125	100	0.040	0.048	0.064	0.080
Duplex (22%)		•	x	o	100	90	0.040	0.048	0.064	0.080
Super Duplex (25%)		•	x	o	75	60	0.040	0.048	0.064	0.080
High Temp Alloys		•	x	x	55	45	0.025	0.030	0.040	0.050
Titanium Alloys	S	•	o	o	115	100	0.040	0.048	0.064	0.080
Gray Cast Irons	K	•	o	o	495	395	0.060	0.072	0.096	0.120
Ductile Cast Irons		•	o	o	295	270	0.060	0.072	0.096	0.120
Malleable Cast Irons		•	o	o	175	150	0.060	0.072	0.096	0.120
Hardened Steels 45-50 HRC	H	o	•	o	185	150	0.050	0.060	0.080	0.100
Hardened Steels 50-55 HRC		o	•	o	155	-	0.035	0.042	0.056	0.070
Hardened Steels 55-60 HRC		o	•	o	100	-	0.020	0.024	0.032	0.040

• Preferred o Possible x Not Possible

Notes:

- For machining materials above 50 HRC, reduce stepover (ae) to 2-3% of DC for optimal performance

Spindle Maximum - Should the calculated spindle speed be more than your actual spindle maximum, use this formula:
 (Calculated Feed x Spindle Maximum)/Calculated Speed.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.